



STYLE 1500 – AFC COMPRESSED SHEET



RECOMMENDED APPLICATIONS: GOOD SEALABILITY; EXCELLENT CHEMICAL RESISTANCE; GOOD GENERAL PURPOSE SHEET.

TEMPERATURE	500° F
COMPRESSIBILITY-ASTM-F-36A	7-17%
RECOVERY-ASTM-F-36J	50% MINIMUM
TENSILE STRENGTH (1/32") ASTM-F	1750psi
CREEP RELAXATION (1/32") ASTM-F-36J	25%
SEALABILITY ASTM-F-38B	.33ML/HR
DENSITY-ASTM-F-37	109.18lb/ft
THICKNESS INCREASE	
-ASTM Oil No.3, 5h, 300°F	0-10%
-ASTM Fuel 8, 5h, 73°F	0-10%
ASTM F140 LINE CALL-OUT	F712122A9E22K9M5
TYPICAL SHEET THICKNESSES	1/64", 1/32", 1/16", 3/32", 1/8"
SHEET SIZES	60" X 60"